Biomaterials Journal
http://www.biomatj.com
Online ISSN: 2812-5045

Type of the Paper (Mini-Review)

Next-Generation Dental Materials: A Mini-Review of Bioactive and Smart Formulations

Rasha M. Abdelraouf [1*]

[1] ***Biomaterials Department, Faculty of Dentistry, Cairo University, Cairo 11553, Egypt.***
* Corresponding author e-mail: rasha.abdelraouf@dentistry.cu.edu.eg

Citation: *Rasha M. Abdelraouf. Next-Generation Dental Materials: A Mini-Review of Bioactive and Smart Formulations . Biomat. J., 4 (4), 5 – 7 (2025).*

*https://doi.org/10.5281/*znodo.5829408

Received: 30 October 2025

Accepted: 12 November 2025

Published: 15 November 2025

Abstract: Dental materials have progressed from passive restoratives, which merely replace lost tissue, to active or intelligent systems that dynamically interact with the oral environment to promote health and prevent disease. This mini-review highlights the core scientific advancements in next-generation dental materials, focusing on bioactive and smart formulations. Bioactive materials are engineered to support natural tissue functions like remineralization and regeneration, while smart materials exhibit a stimuli-responsive capacity (e.g., to pH changes) to release therapeutic agents or modify their properties. These innovations, often leveraging nanotechnology, represent a paradigm shift towards truly restorative and preventive dentistry, aiming to increase the longevity of restorations and address the leading cause of failure: secondary caries.

Keywords: bioactive materials, smart systems, dental restorations, ion-releasing.

Introduction

Traditional dental restorative materials, such as amalgam, conventional resin composites, and ceramics, are largely inert. While offering excellent mechanical properties, their failure to actively combat the persistent challenges of the oral environment—specifically the formation of cariogenic biofilms and the subsequent acidic demineralization—leads to secondary (recurrent) caries, which remains the primary reason for restoration replacement. The development of next-generation materials is motivated by the need to create a functional interface between the restoration and the tooth structure, minimizing material degradation, inhibiting bacterial colonization, and actively contributing to the overall health of the adjacent dental tissues [1].

Scientific Data on Advanced Formulations

The most significant recent scientific developments fall into two key categories, frequently overlapping through the use of advanced manufacturing (e.g., 3D printing) and nanotechnology (the incorporation of nanoparticles).

1. Bioactive Materials

Bioactivity in dental materials refers to their ability to provoke a specific biological response that results in the formation of a mineralized layer similar to enamel on their surface or the release of ions that aid in native remineralization processes [2].

Ion-Releasing Systems: Materials such as bioactive glasses (BGs), which typically contain SiO_2, Na_2O, CaO, and P_2O_5, are engineered to dissolve in a controlled manner when exposed to aqueous environments. This dissolution process releases ions such as Ca^{2+}, PO_4^{3-}, and F^-, which raise the local pH and supersaturate the surrounding fluid with minerals. This promotes the formation of a hydroxyapatite (HAp) layer. The HAp layer can seal micro-gaps at the tooth/restoration margin, preventing bacterial infiltration. In vitro studies have demonstrated that incorporating BGs into resin composites can significantly enhance mineral deposition. This effect is often quantified using Scanning Electron Microscopy (SEM) for morphological analysis and Energy-Dispersive X-ray Spectroscopy (EDX) to verify the chemical composition of the formed HAp layer [3].

Tissue Regeneration: Advancements in bioactive materials extend to those designed to promote dental pulp stem cell (DPSC) differentiation for dentin-pulp complex regeneration, a key aspect of regenerative endodontics. Materials used as capping agents are being modified with growth factors or integrated into hydrogel scaffolds to stimulate odontoblast differentiation. Evidence of this includes increased expression of marker genes such as Dentin Sialoprotein (DSP) and Dentin Matrix Protein 1 (DMP1) in cell culture assays [4].

2. Smart (Stimuli-Responsive) Materials

Smart (Stimuli-Responsive) Materials: These materials are designed to sense environmental changes and respond with pre-programmed therapeutic actions, such as the release of targeted drugs or agents [5].

pH-Responsive Systems: Caries, caused by bacterial acid production, typically leads to a drop in pH. Smart materials are designed to detect this drop and respond accordingly. Polymeric hydrogel networks or nano-reservoirs containing therapeutic agents (e.g., antimicrobials) can swell or degrade at an acidic pH (around 5.5 or lower), characteristic of cariogenic environments. In vitro studies assess the release kinetics by incubating materials in buffers with varying pH levels, such as 7.0 and 5.5. The material's defining characteristic is the sharp increase in drug release at lower pH, ensuring that therapeutic agents are only released when needed, minimizing cytotoxicity, and prolonging the material's efficacy [6].

Antimicrobial Nanoparticles: Incorporating nanoparticles like Silver (AgNPs) and Zinc Oxide (ZnONPs) into composite or adhesive matrices provides broad-spectrum antimicrobial activity to prevent biofilm formation. Research indicates that AgNPs, incorporated at concentrations between 0.1-1.0 wt%, significantly reduce the viability of *Streptococcus mutans*, a key cariogenic bacterium. This effect is typically quantified using colony-forming unit (CFU) assays or live/dead staining, showing up to a 2-log reduction in biofilm load compared to control materials. The particle size, often below 50 nm, is optimized to provide a high surface-area-to-volume ratio, maximizing efficacy without compromising the material's mechanical properties [6].

Conclusion

The evolution of dental materials toward bioactive and smart systems represents a significant advancement in preventative and regenerative oral healthcare. Through the application of precise material engineering, often driven by nanotechnology, these next-generation formulations are designed to proactively address the primary causes of restoration failure—microbial challenges and demineralization. Scientific data confirms that these materials are being successfully engineered to be pH-responsive and ion-releasing, thereby enhancing the restorative process and holding the potential to greatly improve the long-term clinical success and durability of dental restorations. Ongoing research is focused on translating these promising in vitro and ex vivo findings into comprehensive, long-term clinical trials.

References

[1] P. C., C. Prati, and M. G. Gandolfi, "Calcium silicate bioactive cements: Biological perspectives and clinical applications," *Dent. Mater.*, vol. 31, no. 4, pp. 351–370, 2015, doi: http://dx.doi.org/10.1016/j.dental.2015.01.004.

[2] N. Jafari, M. S. Habashi, A. Hashemi, R. Shirazi, N. Tanideh, and A. Tamadon, "Application of bioactive glasses in various dental fields," *Biomaterials Research*, vol. 26, no. 1. 2022. doi: 10.1186/s40824-022-00274-6.

[3] M. Khoroushi and F. Keshani, "A review of glass-ionomers: From conventional glass-ionomer to bioactive glass-ionomer.," *Dent. Res. J. (Isfahan).*, vol. 10, no. 4, pp. 411–20, 2013, [Online]. Available: http://www.ncbi.nlm.nih.gov/pubmed/24130573%0Ahttp://www.pubmedcentral.nih.gov/articlerender.fcgi?artid=PMC3793401

[4] H. Lan, W. Qin, and G. Song, "Research progress on the application of self-assembled peptides in endodontics and periodontitis," *Chinese Journal of Tissue Engineering Research*, vol. 26, no. 10. pp. 1703–1709, 2022. doi: 10.12307/2022.214.

[5] K. Yu *et al.*, "Smart Dental Materials Intelligently Responding to Oral pH to Combat Caries: A Literature Review," *Polymers*, vol. 15, no. 12. 2023. doi: 10.3390/polym15122611.

[6] C. Montoya *et al.*, "Smart dental materials for antimicrobial applications," *Bioact. Mater.*, vol. 24, pp. 1–19, Jun. 2023, doi: 10.1016/J.BIOACTMAT.2022.12.002.